

# FSC® Elliottis Pine Plywood (Brazilian)

## GENERAL DESCRIPTION:

Manufactured from a single specie of Elliottis Pine. The board is normally manufactured with an odd number of plies, each ply being oriented at 90 degrees to those bonded to it, to create a balanced construction. The face and reverse veneers are almost always oriented in the direction of the longest dimension.

<b>Timber Species:</b>	Pinus Elliotti
<b>Board Thickness:</b>	Imported in thicknesses of 9, 12, 18 & 24mm
<b>Standard Size:</b>	2440 x 1220 mm
<b>Bond Class:</b>	EN314-2
<b>Grades Available:</b>	C+/C Touch-sanded & Unsanded C+ (touch-sanded) Solid face containing knots. All open defects are filled and sanded C (unsanded) Permits open knot holes, sound knots and other open defects

## PACKING AND WEIGHTS:

THICKNESS [mm]	BOARDS PER PACK	WEIGHT PER BOARD [kg]
9	100	17.4
12	75	23.2
18	50	34.8
24	36	48.4

Please note: Actual packing quantities may vary.

## PHYSICAL DATA:

<b>Density -</b>	600—680 kg/m <sup>3</sup>
<b>Moisture Content -</b>	10% +/- 3%
<b>Strength Data -</b>	Available on request
<b>Tolerances -</b>	To BS EN 315

**Applications:** Structural and non-structural construction work, site hoardings, boarding up, packaging

## OTHER INFORMATION:

These boards have been tested to meet the basic requirements of the Construction Products Regulation in accordance with EN 13986 and display a CE mark to demonstrate this.

## EUTR COMPLIANCE:

Meyer source Elliottis plywood from sources offering FSC® certification and therefore assess the product as being of negligible risk under EUTR.

